



STAINLESS STEEL 17-4PH

FEATURES

- A precipitation-hardening martensitic stainless steel
- Excellent mechanical properties up to approximately 600 °F (316 °C)
- Good welding & machinability
- Good corrosion resistance

APPLICATIONS

- Medical & Dental
- Defense & Firearms
- Aerospace
- Automotive
- Oil & Gas
- Chemical & food processing industries

POWDER PROPERTIES

Chemical Composition (wt%)	Minimum	Maximum
Element		
Carbon (C)	-	.07
Manganese (Mn)	-	1
Phosphorus (P)	-	.04
Sulfur (S)	-	.03
Silicon (Si)	-	1
Chromium (Cr)	15	17.5
Nickel (Ni)	3	5
Copper (Cu)	3	5
Niobium & Tantalum (Nb+Ta)	.15	.45
Iron (Fe)	Balance	Balance

Other Elements: Total may not exceed 1.0% combined. Same chemical composition as the built parts. In Accordance with MPIF Standard 35 (2016 Edition), and ASTM UNS S17400 (12th Edition).

TYPICAL MATERIAL PROPERTIES

	As-sintered	Heat-treated*	Standard
Ultimate Tensile Strength	1000 MPa (145 ksi)	1317 MPa (191 ksi)	ASTM E8/E8M
Yield Strength (0.2% offset)	750 MPa (109 ksi)	1172 MPa (170 ksi)	
Elongation to Failure	7%	10%	
Elastic Modulus	185 GPa (26.8 msi)	-	
Hardness	34 HRC	42 HRC	ASTM E18
Notched Charpy Impact Energy	19 J (14 ft-lbs)	-	ASTM E26
Relative Density	>99%		ASTM B962
Density	7.68 g/cm ³ (0.278 lbs/in ³)		
Surface Roughness (Ra)	3.0 µm (120 µin)		ASTM B946
Corrosion	Pass		ASTM F1089
Tolerances	± 0.005 in/in		

* Heat treatment condition: H 900. Additional heat treatment options available upon request.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each buyer is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. 3DEO makes no warranties, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement. Product specifications are subject to change without notice. 17-4PH Stainless Steel ©2018 3DEO, Inc. All rights reserved. Rev. 08/2018